

* NOTICES *

JPO and INPIT are not responsible for any damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.**** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] The ion conductivity macromolecule with which a proton acid radical is characterized by being separated from macromolecule principal chain structure by the spacer structure of one or more atoms.

[Claim 2] The ion conductivity giant molecule with which spacer structure which separates a proton acid radical and giant-molecule principal chain structure is characterized by being carbon, a ketone, the ether, a thioether, the silyl ether, an amide, ester, imide, carbonate, and urethane.


[Claim 3] Spacer structure Alkyl, aryl, alkoxy ** aryloxy, A ketone, the ether, a thioether, an aldehyde, an amide, ester, A thiol, cyano ** urethane, a halogen, nitril, carboxyl, Silyl, poly alkene oxy-** poly arylene oxy-** poly arylene sulfate, Claim 1, the ion conductivity macromolecule of two publications which are characterized by being the monomer, the oligomer, or the polymer radical containing the poly arylene sulfone, a poly phenoxyphenyl ketone, polystyrene, polyphenylene, a polyamide, polyimide, polyester, and polyolefine.

[Claim 4] The ion conductivity macromolecule according to claim 1 to 3 with which macromolecule principal chain structure is characterized by having a polyphenylene frame, a polyester frame, the poly alkene oxy-frame, the poly arylene oxy-frame, the poly arylene sulfate frame, the poly arylene sulfone frame, a poly phenoxyphenyl ketone frame, a polystyrene frame, a polyamide frame, a polyimide frame, and a polyolefine frame.

[Claim 5] The ion conductivity macromolecule according to claim 1 to 4 with which a proton acid radical is characterized by being a sulfonic group, a carboxylic-acid radical, a phosphoric-acid radical, and a sulfone imide radical.

[Claim 6] The ion conductivity macromolecule according to claim 1 to 5 characterized by what is expressed with the following general formula (I).

[Formula 1]



(I)

Even if the same the inside R1 and R2 of a formula, it may differ, and an aromatic series ring may be permuted to a maximum of four pieces. Hydrogen, alkyl, aryl, alkoxy ** aryloxy, a ketone, The ether, a thioether, the silyl ether, an aldehyde, an amide, ester, Thiol, cyano ** halogen, and poly alkene oxy-** poly arylene oxy-** Poly arylene sulfate, the poly arylene sulfone, a poly phenoxyphenyl ketone, [whether it is the monomer, the oligomer, or the polymer radical containing polystyrene, polyphenylene, a polyamide, polyimide polyester, and polyolefine, and Y exists and] Or it is chosen out of the group which consists of -Ar-, -Z-, -Z-Ar-, and -Ar-Z-Ar-. here -- Z-O-, -S-, -NR'-, and -O(CO)- and -(CO)NH(CO)- -NR'(CO)-, a phthalimide, PIROMERITTO imide, -CO-, - 'is alkyl or aryl independently, and it may join together and it may suit. CH2-, -CF2-, and -CR'R'' -- the divalent radical chosen from the group which consists of - it is -- here -- R' and R' -- Ar is chosen from the group which consists of arylenes, such as phenyl, naphthalene, and an anthracene, arylene permuted by the hetero arylene list by at least one R group, and hetero arylene. X is a proton acid radical chosen from a sulfonic group, a carboxylic-acid radical, a phosphoric-acid radical, and a sulfone imide radical. n -- one or more integers -- it is -- m -- and -- l It may be zero or more integers and a block or random is [n+m+l at least may be four or more, and] sufficient as each part of n, m, and l.

[Claim 7] The ion conductivity poly membrane characterized by using an ion conductivity macromolecule according to claim 1 to 6.

[Claim 8] The fuel cell characterized by using the ion conductivity macromolecule body membrane of a publication for either according to claim 1 to 7.

[Translation done.]

* NOTICES *

JPO and INPIT are not responsible for any damages caused by the use of this translation.

- 1.This document has been translated by computer. So the translation may not reflect the original precisely.
- 2.**** shows the word which can not be translated.
- 3.In the drawings, any words are not translated.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[Field of the Invention] This invention relates to the ion conductivity macromolecule with the proton acid radical suitable for the film for fuel cells applicable to the fuel cell which uses hydrogen, water, alcohol, etc. for a fuel ion conductivity excelled [macromolecule] in thermal resistance highly.

[0002]

[Description of the Prior Art] In recent years, new energy accumulation of electricity or a generation-of-electrical-energy component has been strongly called for from the point of an environmental problem in society. It is the generation-of-electrical-energy component with which the fuel cell also attracts attention as one of them, and it is most expected from low pollution and the description of being efficient that it is. By oxidizing fuels, such as hydrogen and a methanol, electrochemically using oxygen or air, a fuel cell is changed into electrical energy and takes out the chemical energy of a fuel.

[0003] Such a fuel cell is classified into a phosphoric acid mold, a melting carbonate mold, a solid acid ghost mold, and a polyelectrolyte mold according to the class of electrolyte to be used. The phosphoric acid mold fuel cell is already put in practical use for power. However, the phosphoric acid mold fuel cell needed to be made to act at an elevated temperature (before or after 200 degrees C), therefore since the miniaturization of a system with long warm-up time being difficult and the proton conductivity of phosphoric acid were low, it had the fault that a big current could not be taken out.

[0004] On the other hand, the operating temperature of a macromolecule mold fuel cell is about about 80-100 degrees C in the highest. Moreover, since the internal resistance in a fuel cell can be reduced by making thin the electrolyte membrane to be used, it can be operated with a quantity current, therefore it can miniaturize. Research of a macromolecule mold fuel cell prospers from such an advantage.

[0005] Ion conductivity high about the proton which participates in the electrode reaction of a fuel cell is required of the polyelectrolyte film used for this macromolecule mold fuel cell. As such an ion conductivity polyelectrolyte film ingredient, super-strong acid radical content fluorine system giant molecules, such as a trade name Nafion (Du Pont make) or Dow film (the Dow-Jones company make), are known. However, since these polyelectrolyte ingredients are the macromolecules of a fluorine system, they have the problem of being very expensive. Moreover, since moisture maintenance around 100 degrees C which is operating temperature since the glass transition temperature which these macromolecules have is low was not enough, high ionic conductivity could not be utilized thoroughly, but there was a problem of ionic conductivity falling rapidly and it becoming impossible to act as a cell.

[0006] On the other hand, although giving the residue which is chosen as a polymer from a carboxylic-acid radical, a sulfonic group, and a phosphoric-acid radical and which can be dissociated to ion was indicated by Patent Publication Heisei 8-504293 in order to give ion conductivity, neither about a polymer frame nor ionic conductivity, it was limited at all. Moreover, although were indicated by WO9424717, and the ion conductivity macromolecule characterized

by including phenylene structure in the principal chain containing a proton acid radical showed that the part of a sulfone radical was not pinpointed but ion conductivity was shown, it was a low value.

[0007] When the proton acid radical compounded the ion conductivity macromolecule characterized by being separated from macromolecule principal chain structure by the spacer structure of one or more atoms and evaluated film organization potency and ion conductivity this time, high ion conductivity's being shown and thermal resistance were high, and we found out that especially the ion conductivity macromolecule with which a proton acid radical is characterized by being separated from macromolecule principal chain structure by the spacer structure of one or more atoms was excellent.

[0008]

[Problem(s) to be Solved by the Invention] This invention tends to solve the problem which such a conventional technique has. Namely, ion conductivity aims at offering the ion conductivity poly membrane for fuel cells and fuel cell using an ion conductivity macromolecule with the proton acid radical which was highly excellent in thermal resistance, and this.

[0009]

[Means for Solving the Problem] The ion conductivity poly membrane for fuel cells which this invention offers is characterized by being the ion conductivity macromolecule with which a proton acid radical is characterized by being separated from macromolecule principal chain structure by the spacer structure of one or more atoms.

[0010] The fuel cell concerning this invention is characterized by using the above-mentioned ion conductivity poly membrane.

[0011] The ion conductive polymer film concerning this invention has the high ion conductivity which is satisfactory practically, and is excellent in thermal resistance.

[0012] the low resistance which was excellent in endurance when the fuel cell was formed using the ion conductive polymer film especially applied to this invention -- a high current -- an operational fuel cell can be obtained.

[0013] That is, this invention is specified according to the following matters.

[0014] The ion conductivity macromolecule with which <1> proton-acid radical is characterized by being separated from macromolecule principal chain structure by the spacer structure of one or more atoms.

[0015] The ion conductivity giant molecule with which spacer structure which separates <2> proton-acid radical and giant-molecule principal chain structure is characterized by being carbon, a ketone, the ether, a thioether, the silyl ether, an amide, ester, imide, carbonate, and urethane. <Three> spacer structures Alkyl, aryl, alkoxy ** aryloxy, A ketone, the ether, a thioether, an aldehyde, an amide, ester, A thiol, cyano ** urethane, a halogen, nitril, carboxyl, Silyl, poly alkene oxy-** poly arylene oxy-** poly arylene sulfate, Claim 1, the ion conductivity macromolecule of two publications which are characterized by being the monomer, the oligomer, or the polymer radical containing the poly arylene sulfone, a poly phenoxyphenyl ketone, polystyrene, polyphenylene, a polyamide, polyimide, polyester, and polyolefine.


[0016] The ion conductivity macromolecule according to claim 1 to 3 with which <4> macromolecule principal chain structure is characterized by having a polyphenylene frame, a polyester frame, the poly alkene oxy-frame, the poly arylene oxy-frame, the poly arylene sulfate frame, the poly arylene sulfone frame, a poly phenoxyphenyl ketone frame, a polystyrene frame, a polyamide frame, a polyimide frame, and a polyolefine frame.

[0017] The ion conductivity macromolecule according to claim 1 to 4 with which <5> proton-acid radical is characterized by being a sulfonic group, a carboxylic-acid radical, a phosphoric-acid radical, and a sulfone imide radical.

[0018] The ion conductivity macromolecule according to claim 1 to 5 characterized by what is expressed with the <6> following general formula (I).

[0019]

[Formula 2]



Even if the same the inside R1 and R2 of a formula, it may differ, and an aromatic series ring may be permuted to a maximum of four pieces. Hydrogen, alkyl, aryl, alkoxy ** aryloxy, a ketone, The ether, a thioether, the silyl ether, an aldehyde, an amide, ester, Thiol, cyano ** halogen, and poly alkene oxy-** poly arylene oxy-** Poly arylene sulfate, the poly arylene sulfone, a poly phenoxyphenyl ketone, [whether it is the monomer, the oligomer, or the polymer radical containing polystyrene, polyphenylene, a polyamide, polyimide polyester, and polyolefine, and Y exists, and] Or it is chosen out of the group which consists of -Ar-, -Z-, -Z-Ar-, and -Ar-Z-Ar-. here -- Z -O-, -S-, -NR'-, and - O(CO)- and - (CO) NH(CO)- - NR'(CO)-, a phthalimide, PIROMERITTO imide, -CO-, - 'is alkyl or aryl independently, and it may join together and it may suit. CH₂-, -CF₂-, and - CR'R'' -- the divalent radical chosen from the group which consists of - it is -- here -- R' and R' -- Ar is chosen from the group which consists of arylenes, such as phenyl, naphthalene, and an anthracene, arylene permuted by the hetero arylene list by at least one R group, and hetero arylene. X is a proton acid radical chosen from a sulfonic group, a carboxylic-acid radical, a phosphoric-acid radical, and a sulfone imide radical. n -- one or more integers -- it is -- m -- and -- l It may be zero or more integers and a block or random is [n+m+l at least may be four or more, and] sufficient as each part of n, m, and l.

<7> An ion conductivity macromolecule according to claim 1 to 6 is used. Ion conductivity poly membrane by which it is characterized.

[0020] <8> Fuel cell characterized by using the ion conductivity macromolecule body membrane of a publication for either according to claim. 1 to 7.

[0021]

[Embodiment of the Invention] Hereafter, the ion conductivity macromolecule concerning this invention is explained concretely.

<a general view of an ion conductivity macromolecule> -- the ion conductivity macromolecule with which a proton acid radical is first characterized by being separated from macromolecule principal chain structure by the spacer structure of one or more atoms is explained.


[0022] The spacer structure in this invention means the thing of the structure which has separated a proton acid radical and macromolecule principal chain structure.

[0023] The spacer structure which separates a proton acid radical and macromolecule principal chain structure the ion conductivity macromolecule in this invention Carbon, a ketone, the ether, a thioether, the silyl ether, an amide, Although it is the ion conductivity macromolecule characterized by being ester, imide, carbonate, and urethane and is not restricted especially other than the joining segment of spacer structure, preferably Alkyl, aryl, alkoxy ** aryloxy, a ketone, the ether, A thioether, an aldehyde, an amide, ester, a thiol, cyano ** Urethane, halogen, nitril, carboxyl, silyl, and poly alkene oxy-** Poly arylene oxy-** poly arylene sulfate, the poly arylene sulfone, It is characterized by being the monomer, the oligomer, or the polymer radical containing a poly phenoxyphenyl ketone, polystyrene, polyphenylene, a polyamide, polyimide, polyester, and polyolefine.

[0024] Furthermore, macromolecule principal chain structure is characterized by having a polyphenylene frame, a polyester frame, the poly alkene oxy-frame, the poly arylene oxy-frame, the poly arylene sulfate frame, the poly arylene sulfone frame, a poly phenoxyphenyl ketone frame, a polystyrene frame, a polyamide frame, a polyimide frame, and a polyolefine frame. Although especially the macromolecule principal chain structure in <macromolecule principal chain structure> this invention is not necessarily restricted, it is characterized by including the part expressed with a general formula (I) as basic structure of a more desirable ion conductivity macromolecule.

[0025]

[Formula 3]



(I)

Even if the same the inside R1 and R2 of a formula, it may differ, and an aromatic series ring may be permuted to a maximum of four pieces. Hydrogen, alkyl, aryl, alkoxy ** aryloxy, a ketone, The ether, a thioether, the silyl ether, an aldehyde, an amide, ester, Thiol, cyano ** halogen, and poly alkene oxy-** poly arylene oxy-** Poly arylene sulfate, the poly arylene sulfone, a poly phenoxyphenyl ketone, [whether it is the monomer, the oligomer, or the polymer radical containing polystyrene, polyphenylene, a polyamide, polyimide polyester, and polyolefine, and Y exists, and] Or it is chosen out of the group which consists of -Ar-, -Z-, -Z-Ar-, and -Ar-Z-Ar-. here -- Z -O-, -S-, -NR'-, and - O(CO)- and - (CO) NH(CO)- - NR'(CO)-, a phthalimide, PIROMERITTO imide, -CO-, - 'is alkyl or aryl independently, and it may join together and it may suit. CH₂-, -CF₂-, and - CR'R'' -- the divalent radical chosen from the group which consists of - it is -- here -- R' and R' -- Ar is chosen from the group which consists of arylenes, such as phenyl, naphthalene, and an anthracene, arylene permuted by the hetero arylene list by at least one R group, and hetero arylene. X is a proton acid radical chosen from a sulfonic group, a carboxylic-acid radical, a phosphoric-acid radical, and a sulfone imide radical. n -- one or more integers -- it is -- m -- and -- l It may be zero or more integers and a block or random is [n+m+l at least may be four or more, and] sufficient as each part of n, m, and l.

[0026] [whether the inside Y of the <structure of -Y-> aforementioned (type I) exists, and] Or it is chosen out of the group which consists of -Ar-, -Z-, -Z-Ar-, and -Ar-Z-Ar-. here -- Z -O-, -S-, -NR'-, and - O(CO)- and - (CO) NH(CO)- - NR'(CO)-, a phthalimide, PIROMERITTO imide, -CO-, - 'is alkyl or aryl independently, and it may join together and it may suit. CH₂-, -CF₂-, and - CR'R'' -- the divalent radical chosen from the group which consists of - it is -- here -- R' and R' -- Ar is chosen from the group which consists of arylenes, such as phenyl, naphthalene, and an anthracene, arylene permuted by the hetero arylene list by at least one R group, and hetero arylene.

[0027] Y expressed with said formula (I) more specifically Biphenylene, terphenylene, a quinoline, quinazoline, naphthylene, Anthracenyl, a pyrene, an azulene, a pyridine, a bipyridine, a pyrimidine, They are ester and the amide mold Y in detail to a phenanthrene, a pyrrole, a thiophene, vinylene, diphenyl ether, diphenyl ketone, an indene, and a pan. A desirable example - phenylene-CONH-phenylene - and -(phenylene-COO- phenylene - OCO)-phenylene - - Phenylene carbonyl-phenylene - It is -(phenylene- carbonyl- phenylene- oxo--phenylene- carbonyl-phenylene)-.

[0028] When the polymer of this invention is a block copolymer, it is the repeat unit Y. Oligomer or a polymer segment is formed. The example which is not restricted A polyamide, the poly ARI rate, poly arylene oxide, A polycarbonate, poly dimethylsiloxane, polyester, a polyether ketone, Polyphenylene, permutation polyphenylene, a polyphenylene sulfide, They are polystyrene, polytetrafluoroethylene, poly trifluoro ethylene, polyvinylidene fluoride, polyethylene, a polyvinyl chloride, polyimide, polyether sulphone, a liquid crystal polymer, a polyphenylene sulfide, etc.

[0029] It sets in this specification and poly arylene oxide is Type (-Ar-O-) n. It is meant that it is the all-inclusive name of a polymer. Poly arylene oxide is Pori (2, the 6- dimethyl -1, 4- phenylene oxide), although not necessarily restricted. Pori (2, 6- diphenyl -1, 4- phenylene oxide) Pori (oxy-- 2, 3, 5, 6- tetrafluoro phenylene) And Pori (oxy-- 2, 6- pyridine diyl) is included. Although summarizing various polymers which include phenylene and an oxo-***** carbonyl repeat unit in this specification is not meant and it does not necessarily restrict a polyether ketone, it contains Pori (oxy-- 1, 4- phenyleneoxy - 1, the 4- phenylene carbonyl -1,

4-phenylene) known also as PEEK for the polyether ether ketone, the related polymer PEK, etc. The poly ARI rate is terephthalic-acid or isophthalic acid, bisphenol A (2 and 2'-isopropylidene diphenol) and resorcinol, hydroquinone, 4, and 4'-. It is meant that it is the all-inclusive name of various polymers generated from diol like a dihydroxy biphenyl. The above-mentioned generic name is well known to this contractor. A polyamide is diamine, for example, 1,4-butanediamine, 1,6-hexanediamine, 4, and 4'-, although not necessarily restricted. Methylenedianiline, 1,3-phenylenediamine, 1, and 4-phenylenediamine etc. and the polymer generated from the usual condensation with diacid, for example, an adipic acid, isophthalic acid, a terephthalic acid, succinic acid, etc. are included.

[0030] Although polyester is not necessarily restricted, it contains diol, for example, ethylene glycol, 1,6-hexanediol, a hydroquinone, propylene glycol, a resorcinol, etc. and the polymer generated from the usual condensation with diacid, for example, an adipic acid, isophthalic acid, a terephthalic acid, succinic acid, etc.

[0031] The structure of R2 among the <structure of -R2> above-mentioned type (I) An aromatic series ring may be permuted to a maximum of four pieces. Hydrogen, alkyl, aryl, Alkoxy ** aryloxy, a ketone, the ether, a thioether, the silyl ether, Aldehyde, amide, ester, thiol, cyano ** halogen, and poly alkene oxy-** It is the monomer, the oligomer, or the polymer radical containing poly arylene oxy-** poly arylene sulfate, the poly arylene sulfone, a poly phenoxyphenyl ketone, polystyrene, polyphenylene, a polyamide, polyimide, polyester, and polyolefine.

[0032] Specifically, a hydrogen atom, a halogen, an atom, a hydrocarbon group, heterocyclic compound residue, an oxygen content radical, a nitrogen content radical, an aluminum content radical, a sulfur content radical, and a silicon content radical can be mentioned.

[0033] More specifically, R2 can mention a hydrogen atom, a halogen atom, a hydrocarbon group, heterocyclic compound residue, a hydrocarbon permutation silyl radical, a hydrocarbon permutation siloxy radical, an alkoxy group, an alkylthio group, an aryloxy radical, an arylthio radical, an acyl group, an ester group, a thioester radical, an amide group, an imide radical, the amino group, an imino group, a sulphone ester radical, a sulfonamide radical, a cyano group, a nitro group, a carboxyl group, a sulfonic group, a sulfhydryl group, an aluminum content radical, or a hydroxy group.

[0034] In <structure of spacer> this invention, R1 equivalent to the part of n containing the proton acid radical expressed with said formula (I) may call a connection radical.

[0035] It is the monomer, the oligomer, or the polymer radical which may permute an aromatic series ring to a maximum of four pieces, and contains hydrogen, alkyl, aryl, alkoxy ** aryloxy, a ketone, the ether, a thioether, the silyl ether, an aldehyde, an amide, ester, a thiol, a cyano ** halogen, poly alkene oxy-** poly arylene oxy-** poly arylene sulfate, the poly arylene sulfone, a poly phenoxyphenyl ketone, polystyrene, polyphenylene a polyamide, polyimide, polyester, and polyolefine as structure of R1 As for R1, it is desirable that they are a phenyl group, benzoyl, a phenoxy group, and an alkyl group to carbon numbers 1-20, and it is more desirable that they are a phenoxy group or an alkyl group to carbon numbers 1-20.

[0036] It is characterized by for X being a proton acid radical and being a sulfonic group, a carboxylic-acid radical, a phosphoric-acid radical, and a sulfone imide radical among the <proton acid radical> above-mentioned type (I). A specific functional group may be used independently or two or more kinds of functional groups may be used. A sulfonic group can be used preferably. <the introductory approach of spacer structure> -- although the approach of carrying out the polymerization of the monomer (the following, "spacer mold monomer") in which spacer structure is included as the introductory approach of the spacer structure containing such a proton acid radical can be mentioned, it is not limited to this.

[0037] For example, dichlorophenyl benzenesulfonic acid, a dichlorophenyl naphthalene sulfonic acid, A dichlorophenyl anthracene sulfonic acid, a dibromo phenylbenzene sulfonic acid, A dibromo phenyl naphthalene sulfonic acid, a dibromo phenyl anthracene sulfonic acid, Dichlorophenyl permutation benzenesulfonic acid, a dichlorophenyl permutation naphthalene sulfonic acid, A dichlorophenyl permutation anthracene sulfonic acid, dibromo phenyl permutation benzenesulfonic acid, The monomer whose spacer parts, such as a dibromo phenyl permutation

naphthalene sulfonic acid and a dibromo phenyl permutation anthracene sulfonic acid, are aromatic series radicals or a condensed-ring aromatic series radical monomer, a heterocycle aromatic series radical monomer, [0038] Furthermore, dichlorophenyl methylsulfonic acid, a dichloro phenylethyl sulfonic acid, A dichlorophenyl propyl sulfonic acid, a dichlorophenyl butyl sulfonic acid, A dichlorophenyl pentyl sulfonic acid, a dichlorophenyl hexyl sulfonic acid, A dichlorophenyl octyl sulfonic acid, a dichlorophenyl nonyl sulfonic acid, A dichlorophenyl deca nil sulfonic acid, a dibromo phenylmethyl sulfonic acid, A dibromo phenylethyl sulfonic acid, a dibromo phenylpropyl sulfonic acid, A dibromo phenyl butyl sulfonic acid, a dibromo phenyl pentyl sulfonic acid, The monomer whose spacer parts, such as a dibromo phenyl hexyl sulfonic acid, a dibromo phenyl octyl sulfonic acid, a dibromo phenyl nonyl sulfonic acid, and a dibromo phenyl DEKANIRU sulfonic acid, are alkyl groups or a substituent content alkyl group monomer, [0039] Furthermore, dichloro phenoxy benzenesulfonic acid, a dichloro phenoxy naphthalene sulfonic acid, A dichloro phenoxy anthracene sulfonic acid, dibromo phenoxy benzenesulfonic acid, A dibromo phenoxy naphthalene sulfonic acid, a dibromo phenoxy anthracene sulfonic acid, Dichloro phenoxy permutation benzenesulfonic acid, a dichloro phenoxy permutation naphthalene sulfonic acid, A dichloro phenoxy permutation anthracene sulfonic acid, dibromo phenoxy permutation benzenesulfonic acid, The monomer whose spacer parts, such as a dibromo phenoxy permutation naphthalene sulfonic acid and a dibromo phenoxy permutation anthracene sulfonic acid, are aromatic series oxy-radicals or a condensed-ring aromatic series oxy-radical monomer, a heterocycle aromatic series oxy-radical monomer, [0040] Furthermore, a dichloro phenoxymethyl sulfonic acid, a dichloro phenoxy ethyl sulfonic acid, A dichloro phenoxy propyl sulfonic acid, a dichloro phenoxy butyl sulfonic acid, A dichloro phenoxy pentyl sulfonic acid, a dichloro phenoxy hexyl sulfonic acid, A dichloro phenoxy octyl sulfonic acid, a dichloro phenoxy nonyl sulfonic acid, A dichloro phenoxy DEKANIRU sulfonic acid, a dibromo phenoxymethyl sulfonic acid, A dibromo phenoxy ethyl sulfonic acid, a dibromo phenoxy propyl sulfonic acid, A dibromo phenoxy butyl sulfonic acid, a dibromo phenoxy pentyl sulfonic acid, A dibromo phenoxy hexyl sulfonic acid, a dibromo phenoxy octyl sulfonic acid, The monomer whose spacer parts, such as a dibromo phenoxy nonyl sulfonic acid and a dibromo phenoxy DEKANIRU sulfonic acid, are alkoxy groups, Or it is a substituent content alkoxy group monomer, and the connection radical of this of the spacer section is a ether group. This connection radical may be an ester group, an amide group, a thioether radical, an imino group, a ketone group, and an aromatic series radical still more nearly similarly, and many is sufficient as the sulfonic group contained by the spacer part serving as oligomer and a polymer chain.

[0041] Although the ion conductivity macromolecule characterized by repeating the spacer mold monomer containing the proton acid radical of <manufacture approach of ion conductivity macromolecule> this invention, and containing in a unit is the following, makes and can be compounded, it is not necessary to necessarily follow these approach and conditions.

[0042] in addition, the monomer of the above-mentioned publication -- T. Kanbara T. Kushida N. Saito I and Kuwajima K. Kubota And T. Yamamoto Chemistry Letters, and 1992 and 583 - 586 Indicated nickel (0) reduction coupling using a compound -- Or *****'457 No. or United States patent 5,241,044th By reduction coupling which was indicated by the number and by which the nickel catalyst was carried out, I.Colon, and D.R.Kelsey J. By Org.Chem and reduction coupling using the nickel (0) compound indicated by 1986, 51, and 2627, a polymerization can be carried out so that the polymer of this invention may be generated.

[0043] The ion conductivity giant molecule characterized by repeating the spacer mold monomer containing the proton acid radical of <constituent> this invention, and containing in a unit may be used by kind, or two or more sorts may be blended and used for it. Moreover, it is also possible to use it as a blend with other polymers. Although especially the polymer to blend is not limited, polytetrafluoroethylene, poly trifluoro ethylene, polyvinylidene fluoride, polyethylene, a polyvinyl chloride, polyimide, a polyamide, polyether sulphone, a polyether ether ketone, a liquid crystal polymer, a polyphenylene sulfide, etc. are mentioned, for example. It is more desirable that these polymers have the proton acid radical. In case it is made to blend with these polymers, as for the ion conductivity macromolecule characterized by repeating the spacer mold monomer containing the proton acid radical of this invention, and containing in a unit, being contained 30% or more is

desirable, and it is more desirable. [50% or more of] If there is too little ion conductivity macromolecule characterized by repeating the spacer mold monomer containing the proton acid radical of this invention, and containing in a unit, ionic conductivity cannot fully be demonstrated. Moreover, since the ion conductivity giant molecule characterized by repeating the spacer mold monomer containing the proton acid radical of this invention, and containing in a unit has the high hydrophilic property, when it is made to blend with other polymers, it is in the inclination for the water resisting property in an elevated temperature to become high.

[0044] <Ion conductive polymer film> The ion conductivity macromolecule characterized by repeating the spacer mold monomer containing such a proton acid radical content proton acid radical, and containing in a unit is excellent in thermal resistance, and does not deteriorate in the stable usual state of preservation chemically. The ion conductivity macromolecule characterized by repeating the spacer mold monomer containing still such a proton acid radical, and containing in a unit has the property also physically that reinforcement is high.

[0045] Therefore, the ion conductivity macromolecule characterized by repeating the spacer mold monomer containing the proton acid radical of this invention, and containing in a unit shows film reinforcement sufficient as an ion conductivity poly membrane, and the outstanding engine performance. Moreover, it is not limited to an ion conductivity poly membrane, but you may use it as the other film. For example, they are the electrolysis film for polymer batteries, ion exchange membrane, a filtration membrane, a demarcation membrane, the water absorption film, a surface protective coat, etc. Sufficient film reinforcement here is being able to form self-supported film without a base material, ionic conduction is the phenomenon (based on a chemistry great dictionary) in which ion moves under electric field and a current flows, and the ion conductivity poly membrane means the thing of the poly membrane which shows such a property.

[0046] When the ion conductivity macromolecule characterized by repeating the spacer mold monomer containing the proton acid radical of this invention, and containing in a unit is used as a film-like electrolyte, After dissolving the ion conductivity macromolecule characterized by repeating the spacer mold monomer which contains a proton acid radical as the membranous manufacture approach, and containing in a unit in an organic solvent, it applies on a glass plate. The method of deliquoring and obtaining the film or the method of obtaining the film by direct-heating and pressurizing is mentioned. Especially the organic solvent used here is not limited.

[0047] <Fuel cell> The ion conductivity poly membrane characterized by repeating the spacer mold monomer containing the proton acid radical of this invention again, and containing in a unit is also producible as one film with an electrode. For example, the proton acid radical of this invention The spacer mold monomer to contain Between the electrode layers obtained from the solution which mixed the electrode agent with the ion conductivity polymer solution characterized by repeating the spacer mold monomer containing the proton acid radical of the film and this invention obtained from the ion conductivity macromolecule characterized by containing per repeat, and containing in a unit The ion conductivity polymer solution characterized by repeating the spacer mold monomer containing the proton acid radical of a small amount of this invention, and containing in a unit can be pasted up and obtained by evaporating coating lamination and a solvent thinly. the case where it uses for a fuel cell since the film united with such an electrode can make small interfacial resistance between the ionic conductivity film which is an electrode and an electrolyte -- low -- a cell [****] can be offered. If the ion conductivity giant molecule characterized by repeating the spacer mold monomer containing the proton acid radical of this invention as a solvent used at this time, and containing in a unit dissolves, anything, it will be good and dimethylacetamide, dimethyl sulfoxide, N-methyl pyrrolidone, N-methyl pyrrolidinone, N,N-dimethylacetamide, an anisole, chloroform, a methylene chloride, dimethylformamide, etc. will be mentioned.

[0048] the low resistance which was excellent in endurance since the ion conductivity macromolecule characterized by for the fuel cell concerning this invention repeating the spacer mold monomer containing a proton acid radical, and containing it in a unit was used for the binder of an electrolyte or an electrode -- a high current -- an operational fuel cell can be obtained.

[0049] Next, the fuel cell concerning this invention is explained concretely.

[0050] The built fuel cell consists of the positive electrodes and negative electrodes which are contacted and arranged at the poly membrane which has ion conductivity, and these both sides. The hydrogen of a fuel oxidizes electrochemically in a negative electrode, and generates a proton and an electron. This proton moves the inside of the polyelectrolyte film to the positive electrode with which oxygen is supplied. On the other hand, it passes along the load connected to the cell, and flows to a positive electrode, a proton, oxygen, and an electron react in a positive electrode, and the electron generated with the negative electrode generates water.

[0051] The electrode which constitutes said fuel cell consists of electric conduction material, the binder, and the catalyst.

[0052] As electric conduction material, if it is the electrical conductivity matter, which thing may be used and various metals, a carbon material, etc. will be mentioned. for example, carbon black, activated carbon, graphites, etc., such as acetylene black, are mentioned, and these are independent -- or it is mixed and used.

[0053] Although it is desirable to use the ion conductivity macromolecule characterized by repeating the spacer mold monomer containing the proton acid radical of this invention as a binder, and containing in a unit, other various resin can also be used. In that case, various resin has the desirable fluororesin which has water repellence. Also in a fluororesin, a thing 400 degrees C or less has the more desirable melting point, for example, polytetrafluoroethylene, a TERORAFURUORO ethylene perfluoroalkyl vinyl ether copolymer, etc. are mentioned.

[0054] Although it will not be especially limited if it is the metal which promotes oxidation reaction of hydrogen, and the reduction reaction of oxygen as a catalyst metal, lead, iron, manganese, cobalt, chromium, a gallium, vanadium, a tungsten, a ruthenium, iridium, palladium, platinum, rhodiums, or those alloys are mentioned, for example.

[0055]

[Example] Hereafter, although this invention is explained still more concretely based on an example, this invention is not limited at all by these examples. In addition, the conditions of physical-properties measurement are as follows.

[0056] Ionic conductivity: It inserted into the platinum electrode of the pair with a diameter of 5mm which opposes, and measured by the alternating current impedance method. Equipment used the LCR meter (4285made from HewlettPackard A). Measurement was performed under the temperature of 30 degrees C, and the over-humid conditions by the steam of distilled water.

[0057]

[The synthetic example 1] 2 and 5-dichlorophenol 130.4g (0.8 mols), 77g [of 4-chlorobenzene sulfonic acids] (0.4 mols), 110.4g [of anhydrous potassium carbonate] (0.8 mols), and pyridine 15.8g (0.2 mols), 2g of copper powder, 2g of copper iodide, and 250ml of water were mixed, and it heated under nitrogen-gas-atmosphere mind, and was made to react under 2-hour reflux into the flask which carried out the nitrogen purge. It cooled to the room temperature after that, and the processing back was carried out with sodium-carbonate water, and extraction separation of the oil was carried out by diethylether. Filtration recovered the solid which added the hydrochloric acid to the separated water layer, and precipitated. The solid furthermore collected was dissolved in sodium-hydroxide water, and filtration separated insoluble matter. Filtration recovered the solid which added the acetic acid to the remaining sodium-hydroxide water solution, and precipitated. Furthermore, 13g (10% yield) of 2 and 5-dichloro-4-phenoxy benzenesulfonic acid was obtained by the recrystallizing method after desiccation.

[0058]

[The synthetic example 2] Diethylether (anhydrous) Zinc dust of 325 meshes of inside and marketing 1 It washes twice by the hydrogen chloride of M, next washes twice in diethylether (anhydrous), and after drying in a vacuum or under an inert atmosphere for several hours by about 100 ** - 200 **, activity zinc dust is obtained. If a lump forms while it is dry, the re-sheave of the zinc dust will be carried out to -150 meshes. This ingredient is stored under an inert atmosphere so that it may be used immediately or may isolate from oxygen and hygroscopic moisture.

[0059]

[Example 1] To the round bottom flask which carried out the nitrogen purge, it is a screw (triphenyl phosphine). Nickel chloride 0.213g, 0.19g of sodium iodides Triphenyl phosphine 1.02g Activity zinc dust 0.88g chosen in the synthetic example 2 2, 1.6g (5mmol) of 5-dichloro-4-phenoxy benzenesulfonic acid obtained in the synthetic example 1 Dichlorobenzene 0.74g (5mmol) and anhydrous N-methyl pyrrolidone (NMP) It added. This mixture was stirred at 65 degrees C overnight. Ethanol 100ml which contains HCl for viscous mixture 10% It processed by flowing into inside. The rough product was filtered, and it filtered completely with ethanol and an acetone, and it dried by 120 **, and the 1.3g polymer (A) was obtained.

[0060]

[Example 2] 2, 2.39g (7.5mmol) of 5-dichloro-4-phenoxy benzenesulfonic acid The 1.5g polymer (B) was obtained by the same actuation as an example 1 except having changed into dichlorobenzene 0.37g (2.5mmol).

[0061]

[Example 3] It changed into dichlorobenzene 0.37g (2.5mmol), and the 1.4g polymer (C) was obtained by the same actuation as an example 1 except having added 3 and 4-dichloro benzophenone 0.63g (2.5mmol).

[0062]

[Example 4] It changed into dichlorobenzene 0.37g (2.5mmol), and the 1.3g polymer (D) was obtained by the same actuation as an example 1 except having added 4 and 4'-dichloro benzophenone 0.63g (2.5mmol).

[0063]

[Example 5] Dissolved the obtained powder polymer in N-methyl pyrrolidone (NMP), carried out the cast on the glass substrate, it was made to dry at 230 degrees C, and the poly membrane was obtained. The obtained film was rich in flexibility and tough. About this film, ionic conductivity was measured by the approach of said publication. A result is shown in Table 1.

[0064]

[Table 1]

表 1

使用ポリマー		イオン伝導度 (S/cm)
実施例 1	ポリマー(A)	2.2×10^{-3}
実施例 2	ポリマー(B)	3.1×10^{-2}
実施例 3	ポリマー(C)	2.4×10^{-3}
実施例 4	ポリマー(D)	2.1×10^{-3}

[0065] Table 1 -- examples 1-4 -- the Nafion film (Du Pont make) -- comparing -- an ionic conductivity EQC -- or it raised a little and came out. It was the value which is satisfactory practically.

[0066]

[Effect of the Invention] the low resistance which was excellent in endurance since this invention was constituted as explained above -- a high current -- the polyelectrolyte film which makes an operational fuel cell possible and ion conductivity excelled [film] in thermal resistance highly is offered, and the outstanding fuel cell using it is offered.

[Translation done.]

(19)日本国特許庁 (J P)

(12) 公 開 特 許 公 報 (A)

(11)特許出願公開番号

特開2002-289222

(P2002-289222A)

(43)公開日 平成14年10月4日(2002.10.4)

(51)Int.Cl.⁷

識別記号

F I

テ-マ-ト*(参考)

H 0 1 M 8/02

H 0 1 M 8/02

P 4 J 0 3 2

C 0 8 G 61/10

C 0 8 G 61/10

5 H 0 2 6

H 0 1 M 8/10

H 0 1 M 8/10

審査請求 未請求 請求項の数8 O L (全 9 頁)

(21)出願番号 特願2001-88889(P2001-88889)

(22)出願日 平成13年3月26日(2001.3.26)

(71)出願人 000005887

三井化学株式会社

東京都千代田区霞が関三丁目2番5号

(72)発明者 森園 賢一

東京都千代田区霞ヶ関三丁目2番5号 三井化学株式会社内

(72)発明者 塚本 幸治

千葉県袖ヶ浦市長浦580-32 三井化学株式会社内

Fターム(参考) 4J032 CA03 CA04 CB01 CB03 CB04

CB07 CB08 CB11 CC01 CD02

CD07 CD08 CD09 CE03 CE20

CG01

5H026 AA06 CX05 EE18

(54)【発明の名称】 イオン伝導性高分子およびそれを用いた高分子膜と燃料電池

(57)【要約】 (修正有)

【課題】イオン伝導性が高く耐熱性に優れたプロトン酸基を持ったイオン伝導性高分子、およびこれを利用した燃料電池用イオン伝導性高分子膜および燃料電池を提供することである。

【解決手段】プロトン酸基例えばスルホン酸基、カルボン酸基などが、高分子主鎖構造から1原子以上のスペーサー構造例えばアルキル、ケトン、ニトリル、ポリイミドなどにより隔てられていることを特徴とする高分子を用いる。

(2)

【特許請求の範囲】

【請求項 1】プロトン酸基が、高分子主鎖構造から 1 原子以上のスペーサー構造により隔てられていることを特徴とするイオン伝導性高分子。

【請求項 2】プロトン酸基と高分子主鎖構造とを隔てるスペーサー構造が、炭素、ケトン、エーテル、チオエーテル、シリルエーテル、アミド、エステル、イミド、カーボネート、ウレタンであることを特徴とするイオン伝導性高分子。


【請求項 3】スペーサー構造が、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ウレタン、ハロゲン、ニトリル、カルボキシル、シリル、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマー基であることを特徴とする請求項 1、2 記載のイオン伝導性高分子。

【請求項 4】高分子主鎖構造が、ポリフェニレン骨格、ポリエステル骨格、ポリアルケンオキシ骨格、ポリアリーレンオキシ骨格、ポリアリーレンスルフェート骨格、ポリアリーレンスルホン骨格、ポリフェノキシフェニルケトン骨格、ポリスチレン骨格、ポリアミド骨格、ポリイミド骨格、ポリオレフィン骨格を有することを特徴とする請求項 1～3 記載のイオン伝導性高分子。

【請求項 5】プロトン酸基が、スルホン酸基、カルボン酸基、リン酸基、スルホンイミド基であることを特徴とする請求項 1～4 記載のイオン伝導性高分子。

【請求項 6】下記一般式 (I) で表わされることを特徴とする請求項 1～5 記載のイオン伝導性高分子。

【化 1】



(I)

(式中 R1 および R2 は同じでも異なってもよく、また最大 4 個まで芳香族環を置換してもよく、水素、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエーテル、シリルエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ハロゲン、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマ

ー基であり、Y は存在しないか、または、 $-\text{Ar}-$ 、 $-\text{Z}-$ 、 $-\text{Z}-\text{Ar}-$ 、および $-\text{Ar}-\text{Z}-\text{Ar}-$ からなる群より選ばれ、ここで Z は $-\text{O}-$ 、 $-\text{S}-$ 、 $-\text{NR}'$ 、 $-\text{O}(\text{CO})-$ 、 $-(\text{CO})\text{NH}(\text{CO})-$ 、 $-\text{NR}'(\text{CO})-$ 、フタルイミド、ピロメリットイミド、 $-\text{CO}-$ 、 $-\text{CH}_2-$ 、 $-\text{CF}_2-$ 、および $-\text{CR}'$ 、 R' からなる群より選ばれた 2 個の基であり、ここで R' および R' は独立に、アルキルまたはアリールであり、そしてそれは結合しあってもよく、そして、Ar は、フェニル、ナフタレン、アントラセン等のアリーレン、ヘテロアリーレン並びに少なくとも 1 個の R 基で置換されたアリーレンおよびヘテロアリーレンからなる群より選ばれ、X はスルホン酸基、カルボン酸基、リン酸基、スルホンイミド基から選ばれるプロトン酸基であり、n は 1 以上の整数であり、m および l は 0 以上の整数であり、少なくとも $n+m+l$ は 4 以上であり、n、m、l のそれぞれの部分はブロックでもランダムでもよい。)

【請求項 7】請求項 1～6 に記載のイオン伝導性高分子を用いることを特徴とするイオン伝導性高分子膜。

【請求項 8】請求項 1～7 に記載のいずれかに記載のイオン伝導性高分子体膜を用いることを特徴とする燃料電池。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】本発明は水素、水、アルコールなどを燃料に用いる燃料電池などに適用できる、イオン伝導性が高く耐熱性に優れた、燃料電池用膜に適したプロトン酸基を持ったイオン伝導性高分子に関する。

【0002】

【従来の技術】近年、環境問題の点から新エネルギー蓄電あるいは発電素子が社会で強く求められてきている。燃料電池もその 1 つとして注目されており、低公害、高効率という特徴から最も期待される発電素子である。燃料電池とは、水素やメタノール等の燃料を酸素または空気をを用いて電気化学的に酸化することにより、燃料の化学エネルギーを電気エネルギーに変換して取り出すものである。

【0003】このような燃料電池は、用いる電解質の種類によってりん酸型、熔融炭酸塩型、固体酸化物型および高分子電解質型に分類される。りん酸型燃料電池は、すでに電力用に実用化されている。しかし、りん酸型燃料電池は高温 (200℃前後) で作用させる必要があり、そのため起動時間が長い、システムの小型化が困難であること、またりん酸のプロトン伝導度が低いために大きな電流を取り出せないという欠点を有していた。

【0004】これに対して、高分子型燃料電池は操作温度が最高で約 80～100℃程度である。また、用いる電解質膜を薄くすることによって燃料電池内の内部抵抗を低減できるため高電流で操作でき、そのため小型化が

(3)

3

可能である。このような利点から高分子型燃料電池の研究が盛んになってきている。

【0005】この高分子型燃料電池に用いる高分子電解質膜には、燃料電池の電極反応に関与するプロトンについて高いイオン伝導性が要求される。このようなイオン伝導性高分子電解質膜材料としては、商品名Nafion（デュボン社製）またはDow膜（ダウ社製）などの超強酸基含有フッ素系高分子が知られている。しかし、これらの高分子電解質材料はフッ素系高分子であるために、非常に高価であるという問題を抱えている。また、これらの高分子の持つガラス転移温度が低いために、操作温度である100℃前後での水分保持が十分でないために高いイオン伝導度を生かしきれず、イオン伝導度が急激に低下し電池として作用できなくなるという問題があった。

【0006】一方、イオン伝導性を持たせるためにポリマーにカルボン酸基、スルホン酸基、リン酸基から選ばれる、イオンに解離し得る残基を持たせることが特表平8-504293に記載されているが、ポリマー骨格やイオン伝導度については何等限定されていなかった。また、プロトン酸基を含有した主鎖にフェニレン構造を含むことを特徴とするイオン伝導性高分子は、WO9424717に記載されているが、スルホン基の部位が特定されておらず、イオン伝導性を示すことを示しているものの低い値であった。

【0007】今回、プロトン酸基が、高分子主鎖構造から1原子以上のスペーサー構造により隔てられていることを特徴とするイオン伝導性高分子を合成し、膜形成能およびイオン伝導性を評価してみたところ、高いイオン伝導性を示すこと、また耐熱性が高く、プロトン酸基が、高分子主鎖構造から1原子以上のスペーサー構造により隔てられていることを特徴とするイオン伝導性高分子が特に優れていることを我々は見出した。

【0008】

【発明が解決しようとする課題】本発明はこのような従来技術が持つ問題を解決しようとしたものである。すなわち、イオン伝導性が高く耐熱性に優れたプロトン酸基を持ったイオン伝導性高分子、およびこれを利用した燃料電池用イオン伝導性高分子膜および燃料電池を提供することを目的としている。

【0009】

【課題を解決するための手段】本発明が提供する燃料電池用イオン伝導性高分子膜は、プロトン酸基が、高分子主鎖構造から1原子以上のスペーサー構造により隔てられていることを特徴とするイオン伝導性高分子であることを特徴としている。

【0010】本発明に係る燃料電池は、上記のイオン伝導性高分子膜を用いることを特徴としている。

【0011】本発明に係るイオン導電性高分子膜は、実用上問題ない高いイオン伝導性を有し、かつ耐熱性に優

4

れている。

【0012】特に、本発明に係るイオン導電性高分子膜を用いて燃料電池を形成すると、耐久性に優れた、低抵抗で高電流操作可能な燃料電池を得ることができる。

【0013】すなわち、本発明は以下の事項により特定されるものである。

【0014】＜1＞プロトン酸基が、高分子主鎖構造から1原子以上のスペーサー構造により隔てられていることを特徴とするイオン伝導性高分子。

10 【0015】＜2＞プロトン酸基と高分子主鎖構造とを隔てるスペーサー構造が、炭素、ケトン、エーテル、チオエーテル、シリルエーテル、アミド、エステル、イミド、カーボネート、ウレタンであることを特徴とするイオン伝導性高分子。 ＜3＞スペーサー構造が、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ウレタン、ハロゲン、ニトリル、カルボキシル、シリル、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマー基であることを特徴とする請求項1、2記載のイオン伝導性高分子。


30 【0016】＜4＞高分子主鎖構造が、ポリフェニレン骨格、ポリエステル骨格、ポリアルケンオキシ骨格、ポリアリーレンオキシ骨格、ポリアリーレンスルフェート骨格、ポリアリーレンスルホン骨格、ポリフェノキシフェニルケトン骨格、ポリスチレン骨格、ポリアミド骨格、ポリイミド骨格、ポリオレフィン骨格を有することを特徴とする請求項1～3記載のイオン伝導性高分子。

【0017】＜5＞プロトン酸基が、スルホン酸基、カルボン酸基、リン酸基、スルホンイミド基であることを特徴とする請求項1～4記載のイオン伝導性高分子。

【0018】＜6＞下記一般式（I）で表わされることを特徴とする請求項1～5記載のイオン伝導性高分子。

【0019】

【化2】



(I)

（式中R1およびR2は同じでも異なってもよく、また最大4個まで芳香族環を置換してもよく、水素、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエーテル、シリルエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ハロゲ

50

(4)

ン、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマー基であり、Yは存在しないか、または、 $-Ar-$ 、 $-Z-$ 、 $-Z-Ar-$ 、および $-Ar-Z-Ar-$ からなる群より選ばれ、ここでZは $-O-$ 、 $-S-$ 、 $-NR'$ 、 $-O(CO)-$ 、 $-(CO)NH(CO)-$ 、 $-NR'(CO)-$ 、フタルイミド、ピロメリットイミド、 $-CO-$ 、 $-CH_2-$ 、 $-CF_2-$ 、および $-CR'$ 、 R' からなる群より選ばれた2価の基であり、ここで R' および R'' は独立に、アルキルまたはアリールであり、そしてそれは結合しあってもよく、そして、Arは、フェニル、ナフタレン、アントラセン等のアリーレン、ヘテロアリーレン並びに少なくとも1個のR基で置換されたアリーレンおよびヘテロアリーレンからなる群より選ばれ、Xはスルホン酸基、カルボン酸基、リン酸基、スルホンイミド基から選ばれるプロトン酸基であり、nは1以上の整数であり、mおよび1は0以上の整数であり、少なくとも $n+m+1$ は4以上であり、n、m、1のそれぞれの部分はブロックでもランダムでもよい。

<7>請求項1～6に記載のイオン伝導性高分子を用いることを特徴とするイオン伝導性高分子膜。

【0020】<8>請求項1～7に記載のいずれかに記載のイオン伝導性高分子体膜を用いることを特徴とする燃料電池。

【0021】

【発明の実施の形態】以下、本発明に係るイオン伝導性高分子について具体的に説明する。

<イオン伝導性高分子の概観>まず、プロトン酸基が、高分子主鎖構造から1原子以上のスペーサー構造により隔てられていることを特徴とするイオン伝導性高分子について説明する。

【0022】本発明におけるスペーサー構造とは、プロトン酸基と高分子主鎖構造とを隔てている構造物のことをいう。

【0023】本発明におけるイオン伝導性高分子は、プロトン酸基と高分子主鎖構造とを隔てるスペーサー構造が、炭素、ケトン、エーテル、チオエーテル、シリルエーテル、アミド、エステル、イミド、カーボネート、ウレタンであることを特徴とするイオン伝導性高分子であり、スペーサー構造の連結部分以外は特に制限されることはないが、好ましくは、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ウレタン、ハロゲン、ニトリル、カルボキシル、シリル、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、

6


ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマー基であることを特徴としている。

【0024】さらに高分子主鎖構造が、ポリフェニレン骨格、ポリエステル骨格、ポリアルケンオキシ骨格、ポリアリーレンオキシ骨格、ポリアリーレンスルフェート骨格、ポリアリーレンスルホン骨格、ポリフェノキシフェニルケトン骨格、ポリスチレン骨格、ポリアミド骨格、ポリイミド骨格、ポリオレフィン骨格を有することを特徴としている。

<高分子主鎖構造>本発明における高分子主鎖構造は、特に制限されるわけではないが、より好ましいイオン伝導性高分子の基本構造としては一般式(I)で表わされる部分を含むことを特徴としている。

【0025】

【化3】



(I)

(式中R1およびR2は同じでも異なってもよく、また最大4個まで芳香族環を置換してもよく、水素、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエーテル、シリルエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ハロゲン、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマー基であり、Yは存在しないか、または、 $-Ar-$ 、 $-Z-$ 、 $-Z-Ar-$ 、および $-Ar-Z-Ar-$ からなる群より選ばれ、ここでZは $-O-$ 、 $-S-$ 、 $-NR'$ 、 $-O(CO)-$ 、 $-(CO)NH(CO)-$ 、 $-NR'(CO)-$ 、フタルイミド、ピロメリットイミド、 $-CO-$ 、 $-CH_2-$ 、 $-CF_2-$ 、および $-CR'$ 、 R' からなる群より選ばれた2価の基であり、ここで R' および R'' は独立に、アルキルまたはアリールであり、そしてそれは結合しあってもよく、そして、Arは、フェニル、ナフタレン、アントラセン等のアリーレン、ヘテロアリーレン並びに少なくとも1個のR基で置換されたアリーレンおよびヘテロアリーレンからなる群より選ばれ、Xはスルホン酸基、カルボン酸基、リン酸基、スルホンイミド基から選ばれるプロトン酸基であり、nは1以上の整数であり、mおよび1は0以上の整数であり、少なくとも $n+m+1$ は4以上

(5)

7

であり、n、m、lのそれぞれの部分はブロックでもランダムでもよい。）

【0026】<Y-の構造>前記式(I)中Yは、存在しないか、または、-Ar-、-Z-、-Z-Ar-、および-Ar-Z-Ar-からなる群より選ばれ、ここでZは-O-、-S-、-NR'-、-O(CO)-、-(CO)NH(CO)-、-NR'(CO)-、フタルイミド、ピロメリットイミド、-COO-、-CH₂-、-CF₂-、および-CR'R'-からなる群より選ばれた2価の基であり、ここでR'およびR'は独立に、アルキルまたはアリールであり、そしてそれは結合しあってもよく、そして、Arは、フェニル、ナフタレン、アントラセン等のアリーレン、ヘテロアリーレン並びに少なくとも1個のR基で置換されたアリーレンおよびヘテロアリーレンからなる群より選ばれる。

【0027】より具体的には、前記式(I)で表わされるYは、ビフェニレン、ターフェニレン、キノリン、キナゾリン、ナフチレン、アントラセニル、ピレン、アズレン、ピリジン、ビピリジン、ピリミジン、フェナントレン、ピロール、チオフェン、ピニレン、ジフェニルエーテル、ジフェニルケトン、インデン、さらに詳しくはエステルおよびアミド型Yの好ましい例は、-(フェニレン-CONH-フェニレン)-、-(フェニレン-COO-フェニレン-OCO)-フェニレン-、-(フェニレンカルボニル-フェニレン-カルボニル-フェニレン-オキソ-フェニレン-カルボニル-フェニレン)-である。

【0028】本発明のポリマーがブロックコポリマーであるときに、繰り返し単位Yはオリゴマーまたはポリマーセグメントを形成し、その制限しない例はポリアミド、ポリアリーレート、ポリアリーレンオキシド、ポリカーボネート、ポリジメチルシロキサン、ポリエステル、ポリエーテルケトン、ポリフェニレン、置換ポリフェニレン、ポリフェニレンスルフィド、ポリスチレン、ポリテトラフルオロエチレン、ポリトリフルオロエチレン、ポリフッ化ビニリデン、ポリエチレン、ポリ塩化ビニル、ポリイミド、ポリエーテルスルホン、液晶ポリマー、ポリフェニレンスルフィド等である。

【0029】ポリアリーレンオキシドは、本明細書中において、タイプ(-Ar-O-)nのポリマーの総括的な名称であることが意図される。ポリアリーレンオキシドは、制限するわけではないが、ポリ(2,6-ジメチル-1,4-フェニレンオキシド)、ポリ(2,6-ジフェニル-1,4-フェニレンオキシド)、ポリ(オキシ-2,3,5,6-テトラフルオロフェニレン)およびポリ(オキシ-2,6-ピリジンジイル)を含む。ポリエーテルケトンは、本明細書中において、フェニレン、オキソおよびカルボニル繰り返し単位を含む様々なポリマーを総括することが意図され、制限するわけではないが、ポリエーテルエーテルケトンのためにPEEKとしても知られているポ

8

リ(オキシ-1,4-フェニレンオキシ-1,4-フェニレンカルボニル-1,4-フェニレン)、および関連ポリマーPEK等を含む。ポリアリーレートはテレフタル酸またはイソフタル酸と、ビスフェノールA(2,2'-イソプロピリデンジフェノール)、レソルシノール、ヒドロキノ、4,4'-ジヒドロキシビフェニルのようなジオールとから生成された様々なポリマーの総括的な名称であることが意図される。上記の一般名は当業者によく知られている。ポリアミドは、制限するわけではないが、ジアミン、例えば、1,4-ブタンジアミン、1,6-ヘキサレンジアミン、4,4'-メチレンジアニリン、1,3-フェニレンジアミン、1,4-フェニレンジアミン等と、二酸、例えば、アジピン酸、イソフタル酸、テレフタル酸、琥珀酸等との通常の縮合から生成されたポリマーを含む。

【0030】ポリエステルは、制限するわけではないが、ジオール、例えば、エチレングリコール、1,6-ヘキサレンジオール、ヒドロキノ、プロピレングリコール、レソルシノール等と、二酸、例えば、アジピン酸、イソフタル酸、テレフタル酸、琥珀酸等との通常の縮合から生成されたポリマーを含む。

【0031】<R₂の構造>上記式(I)中、R₂の構造は、最大4個まで芳香族環を置換してもよく、水素、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエーテル、シリルエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ハロゲン、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマー基である。

【0032】具体的には、水素原子、ハロゲン、原子、炭化水素基、ヘテロ環式化合物残基、酸素含有基、窒素含有基、アルミニウム含有基、イオウ含有基、ケイ素含有基を挙げることができる。

【0033】より具体的には、R₂が水素原子、ハロゲン原子、炭化水素基、ヘテロ環式化合物残基、炭化水素置換シリル基、炭化水素置換シロキシ基、アルコキシ基、アルキルチオ基、アリーロキシ基、アリールチオ基、アシル基、エステル基、チオエステル基、アミド基、イミド基、アミノ基、イミノ基、スルホンエステル基、スルホンアミド基、シアノ基、ニトロ基、カルボキシル基、スルホ基、メルカプト基、アルミニウム含有基またはヒドロキシ基等を挙げることができる。

【0034】<スペーサーの構造>本発明において、前記式(I)で表わされるプロトン酸基を含有したnの部分に相当するR₁は、連結基と称することがある。

【0035】R₁の構造としては、最大4個まで芳香族環を置換してもよく、水素、アルキル、アリール、アルコキシ、アリールオキシ、ケトン、エーテル、チオエー

(6)

9

テル、シリルエーテル、アルデヒド、アミド、エステル、チオール、シアノ、ハロゲン、ポリアルケンオキシ、ポリアリーレンオキシ、ポリアリーレンスルフェート、ポリアリーレンスルホン、ポリフェノキシフェニルケトン、ポリスチレン、ポリフェニレン、ポリアミド、ポリイミド、ポリエステル、ポリオレフィン、を含むモノマー、オリゴマーまたはポリマー基である。R 1 は、フェニル基、ベンゾイル基、フェノキシ基、炭素数 1 から 20 までのアルキル基であることが好ましく、フェノキシ基あるいは炭素数 1 から 20 までのアルキル基であることがより好ましい。

【0036】＜プロトン酸基＞上記式 (I) 中、X はプロトン酸基であり、スルホン酸基、カルボン酸基、リン酸基、スルホンイミド基であることを特徴としている。特定の官能基を単独で用いても、2 種類以上の官能基を用いても良い。好ましくはスルホン酸基を用いることができる。

＜スペーサー構造の導入方法＞このようなプロトン酸基を含有したスペーサー構造の導入方法として、スペーサー構造が組み込まれているモノマー（以下、「スペーサー型モノマー」）を重合する方法を挙げることができるが、これに限定されるものではない。

【0037】たとえば、ジクロロフェニルベンゼンスルホン酸、ジクロロフェニルナフタレンスルホン酸、ジクロロフェニルアントラセンスルホン酸、ジブロモフェニルベンゼンスルホン酸、ジブロモフェニルナフタレンスルホン酸、ジブロモフェニルアントラセンスルホン酸、ジクロロフェニル置換ベンゼンスルホン酸、ジクロロフェニル置換ナフタレンスルホン酸、ジクロロフェニル置換アントラセンスルホン酸、ジブロモフェニル置換ベンゼンスルホン酸、ジブロモフェニル置換ナフタレンスルホン酸、ジブロモフェニル置換アントラセンスルホン酸などスペーサー部分が芳香族基であるモノマー、あるいは縮合環芳香族基モノマー、複素環芳香族基モノマー、

【0038】さらにはジクロロフェニルメチルスルホン酸、ジクロロフェニルエチルスルホン酸、ジクロロフェニルプロピルスルホン酸、ジクロロフェニルブチルスルホン酸、ジクロロフェニルペンチルスルホン酸、ジクロロフェニルヘキシルスルホン酸、ジクロロフェニルオクチルスルホン酸、ジクロロフェニルノニルスルホン酸、ジクロロフェニルデカニルスルホン酸、ジブロモフェニルメチルスルホン酸、ジブロモフェニルエチルスルホン酸、ジブロモフェニルプロピルスルホン酸、ジブロモフェニルブチルスルホン酸、ジブロモフェニルペンチルスルホン酸、ジブロモフェニルヘキシルスルホン酸、ジブロモフェニルオクチルスルホン酸、ジブロモフェニルノニルスルホン酸、ジブロモフェニルデカニルスルホン酸などスペーサー部分がアルキル基であるモノマー、あるいは置換基含有アルキル基モノマー、

【0039】さらにはジクロロフェノキシベンゼンスル

10

ホン酸、ジクロロフェノキシナフタレンスルホン酸、ジクロロフェノキシアントラセンスルホン酸、ジブロモフェノキシベンゼンスルホン酸、ジブロモフェノキシナフタレンスルホン酸、ジブロモフェノキシアントラセンスルホン酸、ジクロロフェノキシ置換ベンゼンスルホン酸、ジクロロフェノキシ置換ナフタレンスルホン酸、ジクロロフェノキシ置換アントラセンスルホン酸、ジブロモフェノキシ置換ベンゼンスルホン酸、ジブロモフェノキシ置換ナフタレンスルホン酸、ジブロモフェノキシ置換アントラセンスルホン酸などスペーサー部分が芳香族オキシ基であるモノマー、あるいは縮合環芳香族オキシ基モノマー、複素環芳香族オキシ基モノマー、

【0040】さらにはジクロロフェノキシメチルスルホン酸、ジクロロフェノキシエチルスルホン酸、ジクロロフェノキシプロピルスルホン酸、ジクロロフェノキシブチルスルホン酸、ジクロロフェノキシペンチルスルホン酸、ジクロロフェノキシヘキシルスルホン酸、ジクロロフェノキシオクチルスルホン酸、ジクロロフェノキシノニルスルホン酸、ジクロロフェノキシデカニルスルホン酸、ジブロモフェノキシメチルスルホン酸、ジブロモフェノキシエチルスルホン酸、ジブロモフェノキシプロピルスルホン酸、ジブロモフェノキシブチルスルホン酸、ジブロモフェノキシペンチルスルホン酸、ジブロモフェノキシヘキシルスルホン酸、ジブロモフェノキシオクチルスルホン酸、ジブロモフェノキシノニルスルホン酸、ジブロモフェノキシデカニルスルホン酸などスペーサー部分がアルコキシ基であるモノマー、あるいは置換基含有アルコキシ基モノマーであり、これはスペーサー部の連結基がエーテル基であり、さらには同様にこの連結基がエステル基、アミド基、チオエーテル基、イミン基、ケトン基、芳香族基であってもよく、スペーサー部分がオリゴマー、ポリマー鎖となってもよく、含有するスルホン酸基は多数個でもよい。

【0041】＜イオン伝導性高分子の製造方法＞本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴とするイオン伝導性高分子は以下のようにして合成できるが、必ずしもこれらの方法や条件に従わなくてもよい。

【0042】なお、上記記載のモノマーは T. Kanbara, T. Kushida, N. Saito, I. Kuwajima, K. Kubota, および T. Yamamoto により、Chemistry Letters, 1992, 583 ~ 586 に記載されたニッケル(0) 化合物を用いた還元カップリング、または米国特許第 457 号若しくは米国特許第 5,241,044 号に記載されたニッケル触媒された還元カップリング、I. Colon, D.R. Kelsey により、J. Org. Chem, 1986, 51, 2627 に記載されたニッケル(0) 化合物を用いた還元カップリングにより、本発明のポリマーを生成するように重合することができる。

【0043】＜組成物＞本発明のプロトン酸基を含有す

(7)

11

るスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子は、一種で使用する、複数種をブレンドして使用しても良い。また、他のポリマーとのブレンドとして使用することも可能である。ブレンドするポリマーは特に限定されないが、例えば、ポリテトラフルオロエチレン、ポリトリフルオロエチレン、ポリフッ化ビニリデン、ポリエチレン、ポリ塩化ビニル、ポリイミド、ポリアミド、ポリエーテルスルホン、ポリエーテルエーテルケトン、液晶ポリマー、ポリフェニレンスルフィド、などが挙げられる。これらのポリマーがプロトン酸基を有していることがより好ましい。これらのポリマーとブレンドさせる際、本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子は30%以上含まれることが好ましく、50%以上がより好ましい。本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子が少な過ぎるとイオン伝導度を十分に発揮できない。また、本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子は親水性が高いため、他のポリマーとブレンドさせると高温での耐水性が高くなる傾向にある。

【0044】＜イオン導電性高分子膜＞このようなプロトン酸基含有プロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子は、耐熱性に優れ、かつ化学的に安定で通常の保存状態で劣化することもない。さらにこのようなプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子は物理的にも強度が高いという特性を有している。

【0045】そのため、本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子はイオン伝導性高分子膜として十分な膜強度と優れた性能を示す。また、イオン伝導性高分子膜に限定されず、それ以外の膜として使用しても構わない。たとえば、ポリマー電池用電解膜、イオン交換膜、濾過膜、分離膜、水吸収膜、表面保護膜などである。ここでいう十分な膜強度とは支持体なしで自立膜を形成できることであり、イオン伝導とは、電場下でイオンが移動して電流が流れる現象（化学大辞典による）であり、イオン伝導性高分子膜とはそのような性質を示す高分子膜のことを意味している。

【0046】本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子を膜状の電解質として用いる場合、膜の製造方法としてはプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子を有機溶剤に溶解させた後、ガラスプレート上に塗布して、脱溶媒して膜を得る方

12

法、あるいは直接加熱・加圧することにより膜を得る方法などが挙げられる。ここで用いられる有機溶剤は特に限定されるものではない。

【0047】＜燃料電池＞また、本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子膜は電極との一体膜として作製することも出来る。例えば本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子から得られた膜と本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子溶液と電極剤を混合した溶液から得られる電極膜の間に少量の本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子溶液を薄く塗り張り合わせ、溶媒を蒸発させることで接着して得ることが出来る。このような電極と一体化した膜は、電極と電解質であるイオン伝導度膜間の界面抵抗を小さくできるため、燃料電池に用いた場合に低抵抗な電池を提供する。このとき用いられる溶媒としては、本発明のプロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子が溶解するものならば何でもよく、ジメチルアセトアミドやジメチルスルホキシド、N-メチルピロリドン、N-メチルピロリジノン、N,N-ジメチルアセトアミド、アニソール、クロロホルム、塩化メチレン、ジメチルホルムアミドなどが挙げられる。

【0048】本発明に係る燃料電池は、プロトン酸基を含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子を電解質や電極の結着剤に使用しているため、耐久性に優れた、低抵抗で高電流操作可能な燃料電池を得ることができる。

【0049】次に本発明に係る燃料電池について具体的に説明する。

【0050】係る燃料電池はイオン伝導性を有する高分子膜とこの両側に接触して配置される正極および負極から構成される。燃料の水素は負極において電気化学的に酸化されて、プロトンと電子を生成する。このプロトンは高分子電解質膜内を酸素が供給される正極に移動する。一方、負極で生成した電子は電池に接続された負荷を通り、正極に流れ、正極においてプロトンと酸素と電子が反応して水を生成する。

【0051】前記燃料電池を構成する電極は、導電材、結着剤および触媒から成っている。

【0052】導電材としては、電気伝導性物質であればいずれのものでもよく、各種金属や炭素材料などが挙げられる。例えばアセチレンブラック等のカーボンブラック、活性炭および黒鉛等が挙げられ、これらが単独あるいは混合して使用される。

【0053】結着剤としては、本発明のプロトン酸基を

(8)

13

含有するスペーサー型モノマーを繰り返し単位に含むことを特徴としているイオン伝導性高分子を用いるのが好ましいが、他の各種樹脂を用いることもできる。その場合、各種樹脂は撥水性を有するフッ素樹脂が好ましい。フッ素樹脂の中でも融点が400℃以下のものがより好ましく、例えばポリテトラフルオロエチレン、テトラフルオロエチレン-パーフルオロアルキルビニルエーテル共重合体などが挙げられる。

【0054】触媒金属としては、水素の酸化反応および酸素の還元反応を促進する金属であれば特に限定されないが、例えば鉛、鉄、マンガン、コバルト、クロム、ガリウム、バナジウム、タングステン、ルテニウム、イリジウム、パラジウム、白金、ロジウムまたはそれらの合金が挙げられる。

【0055】

【実施例】以下、本発明について実施例に基づいてさらに具体的に説明するが、本発明は、これらの実施例により何等限定されるものではない。なお、物性測定の方法は次の通りである。

【0056】イオン伝導度：直径5mmの対抗する一対の白金電極にはさんで、交流インピーダンス法で測定した。装置はLCRメーター（Hewlett Packard社製4285A）を使用した。測定は、温度30℃、蒸留水の蒸気による過湿条件下で行った。

【0057】

【合成例1】窒素置換したフラスコ中に、2、5-ジクロロフェノール130.4g（0.8mol）、4-クロロベンゼンスルホン酸77g（0.4mol）、無水炭酸カリウム110.4g（0.8mol）、ピリジン15.8g（0.2mol）、銅粉末2g、ヨウ化銅2g、水250mlを混合し、窒素雰囲気下で加熱し2時間還流下反応させた。その後室温に冷却し、炭酸ナトリウム水で処理後、ジエチルエーテルで油分を抽出分離した。分離した水層に塩酸を加え、沈殿した固形物を濾過により回収した。さらに回収した固形物を水酸化ナトリウム水に溶解させ、不溶物を濾過により分離した。残った水酸化ナトリウム水溶液に酢酸を加え沈殿した固形物を濾過により回収した。さらに乾燥後、再結晶法により2、5-ジクロロ-4-フェノキシベンゼンスルホン酸13g（10%収率）を得た。

【0058】

【合成例2】ジエチルエーテル（無水）中、市販の325メッシュの亜鉛ダストを1Mの塩化水素で2回洗浄

14

*し、次に、ジエチルエーテル（無水）中で2回洗浄し、そして真空中または不活性雰囲気下で約100℃～200℃で数時間乾燥した後に活性亜鉛ダストを得る。もし乾燥している間に塊が形成するならば、亜鉛ダストを-150メッシュに再シーブする。この材料は即座に使用するか、または、酸素および湿分から隔離するように不活性雰囲気下で貯蔵する。

【0059】

【実施例1】窒素置換した丸底フラスコに、ビス（トリフェニルホスフィン）ニッケルクロリド0.213g、ヨウ化ナトリウム0.19g、トリフェニルホスフィン1.02g、合成例2で選られた活性亜鉛ダスト0.88g、合成例1で得られた2、5-ジクロロ-4-フェノキシベンゼンスルホン酸1.6g（5mmol）、ジクロロベンゼン0.74g（5mmol）および、無水N-メチルピロリドン（NMP）を加えた。この混合物を65℃で一晩攪拌した。粘性の混合物を、10%HClを含むエタノール100ml中に注ぐことにより処理した。粗生成物を濾過し、エタノールおよびアセトンで完全に濾過し、そして120℃で乾燥して1.3gのポリマー（A）を得た。

【0060】

【実施例2】2、5-ジクロロ-4-フェノキシベンゼンスルホン酸2.39g（7.5mmol）、ジクロロベンゼン0.37g（2.5mmol）に変えた以外は、実施例1と同様な操作で1.5gのポリマー（B）を得た。

【0061】

【実施例3】ジクロロベンゼン0.37g（2.5mmol）に変え、3、4-ジクロロベンゾフェノン0.63g（2.5mmol）を加えた以外は、実施例1と同様な操作で1.4gのポリマー（C）を得た。

【0062】

【実施例4】ジクロロベンゼン0.37g（2.5mmol）に変え、4、4'-ジクロロベンゾフェノン0.63g（2.5mmol）を加えた以外は、実施例1と同様な操作で1.3gのポリマー（D）を得た。

【0063】

【実施例5】得られた粉末ポリマーをN-メチルピロリドン（NMP）に溶解させ、ガラス基板上にキャストし、230℃で乾燥させ高分子膜を得た。得られた膜は可とう性に富み、強靱であった。この膜について、前記記載の方法でイオン伝導度を測定した。結果を表1に示す。

【0064】

【表1】

表1

使用ポリマー		イオン伝導度(S/cm)
実施例1	ポリマー(A)	2.2×10^{-3}
実施例2	ポリマー(B)	3.1×10^{-2}
実施例3	ポリマー(C)	2.4×10^{-3}
実施例4	ポリマー(D)	2.1×10^{-3}

【0065】表1より、実施例1～4はNafion膜（デュポン社製）比べてイオン伝導度同等あるいはやや

(9)

15

高めであった。実用上問題のない値であった。

【0066】

【発明の効果】本発明は、以上に説明したように構成されているので、耐久性に優れた、低抵抗で高電流操作可

16

能な燃料電池を可能とする、イオン伝導性が高く耐熱性に優れた高分子電解質膜を提供し、それを用いた優れた燃料電池を提供する。